

















MURA

| | |
|---------------------------------------------------|----------------|
| Grammatura m2 / Mass per unit area m ² | 220g/m2 +/- 5% |
| Composizione / Composition | 100% Polyester |
| Larghezza utile / Usable width of roll | min. 140cm |
| Tipo di tessuto / Type of fabric | Woven fabric |

| FULL TESTS ACCORDING TO DIN EN 14465:2006 | | | | Good ←————→ Poor | | | | RESULTS | |
|-------------------------------------------------------------------------------------|----------------------------------------------------------------------------|---------------------------------------------------------------------------------|---------------------------------------------------------------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|---------------------------------------------------------------------------------------|
| | | | CAT. A | CAT. B | CAT. C | CAT. D | | | |
|  | Resistenza alla rottura Tensile Strength | EN ISO 13934-1:2013 | 1433-1583 N WARP 1384-1530 N WEFT | >600 | ≥400 | ≥350 | ≥250 | A/A | |
|  | Test Martindale Abrasion resistance | EN ISO 12947-1:2007; EN ISO12947-2:2017 | 70000-80000 | ≥35000 | 12000-30000 | 4000-10000 | - | A | |
|  | Resistenza allo strappo Tear growth resistance | EN ISO 13937-3:2002 | 61-68 N WARP 61-68 N WEFT | ≥40 | ≥30 | ≥25 | ≥20 | A/A | |
|  | Resistenza allo scorrimento dei fili Resistance to seam slippage | EN ISO13936-2:2004 180 N LOAD | 2,8-3,2 mm WARP 2,8-3,2 mm WEFT | ≤4 | ≤6 | ≤8 | - | A/A | |
|  | Tendenza all'infeltrimento e creazione dei pallini Pilling resistance | EN ISO 12945-2:2021 2000cycles | 4-5 | ≥4-5 | 4 | 3-4 | 3 | A | |
|  | Resistenza allo scolorimento: luce artificiale Colour fastness to light | EN ISO 105 B02:2014-11 | 3-4 | ≥6 | 5 | 4 | - | C | |
|  | Resistenza all'attrito secco Rubbing solvents | EN ISO 105-X12:2016 | 4-5 | ≥4-5 | 4 | 3-4 | - | A | |
|  | Resistenza all'attrito umido Rubbing fastness in humid state | EN ISO 105-X12:2016 | 4-5 | ≥3-4 | 3 | 2-3 | - | A | |
|  | Infiammabilità Ignitability | EN1021 -1 BS5852: Part 1:1979 Ignition source 0 (Cigarette) CAL TB 117 | | | | | | Passed - no burning identified | |
|  | Fire Protection | BS 5852: Part 1: 1979, Ignition source 1 EN1021 - 2 (Match) | Superato - nessuna bruciatura identificata Additional service | | | | | | |
| | Modalità di conservazione Care labeling | | |  |  |  |  |  |  |



1. The pilling of fabrics is a natural process and may not be completely eliminated.
2. In case of fabric catching on sharp objects, the yarn may come out.
3. Pigments migration from fabrics of intensive and dark colours into light-coloured fabrics is unavoidable and is a natural phenomenon.
4. The operation of uv light and sources of heat may cause fabric discolouration (this refers mainly to intensive colours).
5. A fabric which has just been taken off a roll may be creased and wavy, which is a typical phenomenon.
6. In order to avoid creasing and waving, a fabric must be stored lying horizontally, facing one direction. Long-term fabric storage under pressure may result in its irreversible creasing, particularly in the case of cut-thread fabric, such as velvet.
7. The shimmering and shading effect is a natural phenomenon, particularly for velvet.
8. It is recommended to avoid local pressure on the surface of a fabric, as it may result in the fabric splitting apart, irreversible stretching or tearing.
9. Owing to technological reasons, the hue of a fabric may differ from the sample presented in the catalogue by one tone. The catalogue is not a commercial offer.
10. The terms and conditions of complaints may be found on the website: www.davis.pl.
11. The figures used in the fabrics descriptions refer to average values calculated from the test results of several fabric samples, unless otherwise specified.
12. The furniture manufacturer is responsible for adequate seam and needle selection for the respective fabric and furniture shape, as well as for the consequences of their decisions.
13. The fabrics fulfil the requirements of the eu regulation concerning hazardous chemicals (REACH) no 1907/2006, annex XVII.